

SectionTitle

Number

04 00 00 MASONRY

04 01 00 Maintenance of Masonry

04 01 20 Maintenance of Masonry

04 05 13 Masonry Mortaring

04 05 23 Masonry Accessories

04 20 00 UNIT MASONRY

04 21 00 Clay Unit and Brick Veneer

04 22 00 CONCRETE UNIT MASONRY

04 23 00 GLASS UNIT MASONRY

04 40 00 STONE ASSEMBLIES

04 42 00 Exterior Stone Cladding

04 43 00 Stone Masonry

Section Title

Number

04 00 00 MASONRYPart 1 – GeneralSample Panels/ Mock up Walls

For all new and infill masonry work adjacent to existing walls, a 36 square foot sample wall (mock up) is required to be constructed on site near the proposed work area to evaluate the selected brick and the cured mortar colors for matching. Allow for a minimum of 3 weeks curing time to elapse prior to evaluation of the mortar color.

On new construction, a minimum 36 square foot sample wall (mock up) is required to establish the standard of acceptance for all elements of the work, including but not limited to: window and door frame installation details, mortar color, flashing, coursing, pattern, control joints, tie-in with other materials and finishes, accessories, etc. This sample wall is required for all masonry work whether brick, CMU or stone is proposed. The sample panel shall be approved by Owner and the Design Professional prior to ordering materials and commencement of masonry work. Allow for a minimum of 3 weeks curing time to elapse prior to evaluation of the mortar color.

Cold Weather Masonry

Masonry work shall conform to the latest revision to the following standards for cold weather masonry work: *Building Code Requirements for Masonry Structures* (ACI 530.1 /ASCE 6/ TMS 602).

These standards list the preparation, installation and protection procedures necessary when constructing masonry in cold weather.

1. Specification for Masonry Structures (ACI 530.1/ASCE 6/TMS 602)
2. Cold Weather Masonry Construction, PCA IS248
3. Hot and Cold Weather Masonry Construction, PCA LT232 (published by the Masonry Industry Council)

In general, when the ambient temperature is less than forty degrees F. masonry work shall not be constructed without heat, heated materials, and/or protection.

Hot Weather Masonry

Masonry work shall conform to the following standards for hot weather construction *Building Code Requirements for Masonry Structures* (ACI 530/ASCE 5/TMS 402). In general, this means that when the ambient temperature is greater than 100 degrees F (or 90 degrees F with 8 mph wind), masonry work shall not be constructed without

Section Title
Number

consideration for cooling masonry, controlling moisture uptake from units, and providing moist curing as well as necessary mortar protection.

In all cases with masonry work, the low humidity typical of the mountain campus environment leads to masonry units with high suction rates. Masons should test for and adjust the moisture of masonry units by wetting them to compensate for low humidity and high suction rates. The amount of wetting will depend on the rate of absorption of the brick at the time of installment. When being laid, the brick shall have suction sufficient to hold the mortar and to pull the excess water from the mortar, and shall be sufficiently damp so that the mortar will remain plastic enough to permit the brick to be leveled and plumbed after being laid without breaking the mortar bond.

The type of mortar joint should be specified. Tooled joints are required. Raked and weathered joints (or any joints which leave an exposed horizontal masonry unit edge at the joint) are not permitted for exterior masonry.

Controlling efflorescence

Design Professional should design to prevent efflorescence and include construction specifications for moisture protection during construction for all masonry. Designs shall prevent moisture from entering finished masonry walls with flashing and avoid unprotected horizontal sills. Designs shall seal out moisture, and every feature should drain or dry without absorbing moisture. Design wall systems with appropriate measures to prevent moisture transfer from building interiors. Include initial cleaning of masonry by the mason or contractor after first winter after building acceptance in contract specifications.

The tops of all exposed masonry walls shall receive a watertight cap or coping, i.e., sheet metal or precast concrete, to prohibit moisture infiltration and efflorescence.

Part 2 – Products

N/A

Part 3 - Execution

Masonry work that does not conform to the following tolerances shall be repaired or replaced. Tolerances are based on ACTUAL DIMENSIONS.

- Variations from plumb.
- In lines or surfaces of columns, walls, and arises: in 10 feet - $\frac{1}{4}$ "; in any story or 20 feet maximum - $\frac{3}{8}$ "; in four stories or more - $\frac{1}{2}$ ".

Section Title
Number

- For external corners, control joints and other conspicuous lines: in any story or 20 feet maximum - $\frac{1}{4}$ " ; in 40 feet or more - $\frac{1}{2}$ ".
- Variations from the level or the grades indicated on the drawings:
- For exposed lintels, sills, parapets, horizontal grooves and other conspicuous lines: in any bay or 20 feet maximum - $\frac{1}{4}$ " ; in 40 feet or more - $\frac{1}{2}$ ".
- Variation of the linear building lines from established position in plan and related portion of columns, walls and partitions.
- In any bay or 20 feet maximum - $\frac{1}{2}$ " ; in 40 feet or more - $\frac{3}{4}$ "
- Variation in cross-sectional dimensions of columns and in the thickness of walls is plus or minus $\frac{1}{4}$ ".

04 01 00 Maintenance of Masonry

04 01 20 Maintenance of Masonry

Part 1 – General

N/A

Part 2 – Products

N/A

Part 3 – Execution

Cleaning

All masonry work shall be cleaned and sealed before final inspection and acceptance. Acid wash is **not** usually an acceptable method of cleaning. Contractor shall be required to submit proposed procedures and to provide samples of materials where cleaning methods have been tested prior to beginning cleaning operations.

Restoration

Masonry restoration on any building in the designated historic district must comply with Arizona Historical Society requirements. Special attention shall be paid to match existing stone, brick, mortar colors and mortar joints.

Repair and Replacement

Extra stock materials shall be provided per NAU Technical Standards Section 01 78 46 Extra Stock materials.

04 05 13 Masonry Mortar

Part 1 – General

Section Title
Number

All mortar used for masonry construction shall meet the mortar and proportion specifications of ASTM C270. For re-pointing historic structures, DP shall evaluate structural integrity and justify mortar choices using test results for the adjacent masonry units. Type S, N, or O may be selected. Choosing a mortar that is stronger than the masonry may result in cracking of brick or stone units.

Part 2 – Products

N/A

Part 3 - General

Mortar Coloring Materials

Mortar colorants require Owner approval. Final color selection shall be determined from review of a selection of mock-up panels to be constructed by the Contractor. Mock-up panels shall remain on-site for job duration. Premixed/proportioned mortars ordered in large quantities and stored in bags or in a silo on site are recommended for colored mortars. Addition of color to mortar by hand or by the shovel method results in inconsistency in mortar color and is prohibited.

04 05 23 Masonry Accessories

Part 1 – General

Masonry Anchors and Tie Systems

Anchors or ties (including veneer anchors) embedded within masonry systems shall be galvanized and placed in such a way that they are completely covered with mortar.

Design Professional to include anchoring and mechanical fastening details in masonry drawings per structural evaluation and design of wall systems.

Design anchors and ties for steel stud, concrete and concrete masonry unit walls. Veneer back-up for concrete masonry units, or structural steel studs will include a 3/4" substrate/backerboard. Owner has pre-approved the following manufacturers to be in compliance with these standards: "WonderBoard".

Control Joints

Control joints shall be incorporated into straight wall masonry construction which exceeds forty feet. Spacing of control joints shall be specified by the DP. Control and expansion joints widths shall be not less than 3/8" to allow for installation of backer rod and sealant.

Joint Reinforcement

Joint reinforcement is required and shall meet the seismic requirement detailed in the International Building Code. A minimum of nine gauge, mill galvanized horizontal wire reinforcing is required.

Section Title
Number

Flashing

Provide designs for through-wall concealed flashing at all shelf angles, lintels, ledges and other obstructions to cause downward flow of moisture within the wall. Inspection will be required prior to covering over flashing to confirm proper placement. Flashing above doors, mechanical room louvers, and windows to be seamless and end dammed. Detail all through wall flashing to prevent contact with sealant.

Weepholes

A minimum of ¼ inch diameter by four-inch-long polyethylene plastic tubing for weep holes.

Lintels

Provide masonry or steel lintels wherever openings are more than one-foot wide for brick size units and two foot for block size units. Provide steel, precast or formed-in-place masonry lintels for all larger openings. Cure precast lintels before handling and installation. Provide appropriate formwork and false work support for formed-in-place lintels.

Caulking and Sealants

Waterproofing sealer shall have a minimum of five years guarantee for performance without breakdown from UV exposure.

All joints that require a caulking should receive special attention during construction. All joints are to be filled as soon as possible during construction and noted on the as built plans to be included in a FS Maintenance Program.

Admixtures

The use of mortar or grout admixtures, other than color pigments, shall not be allowed. Specifically prohibit the use of any mortar retarding agents due to their unpredictable nature.

Part 2 – Products

N/A

Part 3 - General

N/A

****END OF SECTION****

Section Title

Number

04 20 00 UNIT MASONRYPart 1 – General

Unit masonry selected for building exteriors shall be in accordance with the Owner's materials palette.

Finished unit masonry shall be, and shall remain, free from efflorescence and discoloration. Precautions to ensure this shall include: materials handling (storage of masonry on pallets with covers to keep masonry clean and dry), covering unfinished work and protection from moisture, sealants such as blocktite or mortar mixes, washing and waterproofing of walls, and specification of ASTM Test E-67 (efflorescence test) on large projects. Brick and concrete unit installations shall carry a two-year warranty against efflorescence.

Part 2 – Products

N/A

Part 3 – Execution

Composite walls with integral insulation are the preferred for walls with exterior masonry. Walls may be steel stud, cast-in place or precast concrete or concrete masonry unit structural walls with a brick, CMU, or stone veneer. Wall designs will include a moisture management system to direct water away from wall crown this includes roofs and overhangs for covered walls and precast concrete or metal copings for parapets. Slope sills, projections and other horizontal surfaces and to carry moisture out from walls.

A two-inch minimum air space shall be maintained between face brick and cavity insulation. Cavity shall be unobstructed, free from mortar drippings.

Workmanship

All mortar joints should be full joints.

Partially completed walls should be covered at the end of each working day, or when work is not in progress, with a strong weather resistant material to prevent contamination. Covers shall drape over both sides and be securely fastened.

All materials should be stored in a dry area. To prevent contamination of materials, masonry units, cements, limes and sand should not be stored on the ground.

Attic Stock

Extra stock materials shall be provided in accordance with the NAU Technical Standards Section 01 78 46 Extra Stock materials.

SectionTitle

Number

04 21 00 Clay Unit and Brick VeneerPart 1 – GeneralBrick Masonry

Brick selected for building exteriors shall be in accordance with the Owner's materials palette.

Materials shall conform to ASTM standard specifications including C216 (Facing Brick), C652 (Hollow Brick) and C270 (Mortar for Unit Masonry) C62 (Building Brick), ASTM C902 (Pedestrian and Light Traffic Paving Brick). All materials shall be rated for Severe Weathering or (SW) class.

Wall designs will include a moisture management system to direct water away from wall crown this includes roofs and overhangs for covered walls and precast concrete or metal copings for parapets.

Slope sills, projections and other horizontal surfaces and to carry moisture out from walls.

Part 2 – Products

N/A

Part 3 - Execution

To minimize brick color variations, the project's brick masonry and brick veneer masonry should be fired and supplied in one continuous run. If variations in color exist within the run, the differently shaded bricks shall be randomly intermixed as the wall is constructed. Obvious delineations in the brick color are not acceptable. Sample panel shall include an example pattern of intermixed or same run brick.

04 22 00 Concrete Unit MasonryPart 1 – General

Concrete unit masonry is an accepted method of construction. Decorative CMU's, splitface, or founders block are some types of concrete units currently in use.

Pedway Construction

Concrete unit paving stones are preferred for flat work in traffic areas (see section 32 13 16 for details), especially for pedway construction. Colors and unit type shall be consistent with those currently in use.

Part 2 – Products

N/A

SectionTitle
Number

Part 3 - Execution
N/A

04 23 00 Glass Unit Masonry

Part 1 – General

Glass unit masonry (glass block) selected for building exteriors shall be in accordance with Owner’s materials palette.

Part 2 – Products
N/A

Part 3 - Execution
N/A

****END OF SECTION****

SectionTitle

Number

04 40 00 STONE ASSEMBLIESPart 1 – General

Stone selected for building exteriors shall be in accordance with the Owner's materials palette.

All exterior stone veneer shall be designed to use mechanically fastened stone rather than adhesive attachment for its primary attachment method. The preferred backing wall is CMU.

Part 2 – Products

N/A

Part 3 - Execution

N/A

04 42 00 Exterior Stone CladdingPart 1 – General

All exterior stone cladding shall be designed to use mechanically fastened stone rather than adhesive attachment for its primary attachment method.

Part 2 – Products

N/A

Part 3 - Execution

N/A

04 43 00 Stone MasonryPart 1 – General

Stone masonry walls are composite walls and shall be constructed in conformance with 04 20 00.

Part 2 – Products

N/A

Part 3 - Execution

N/A

****END OF SECTION****